



SLOPE DECK Properly Prepared Substrate/  
 $\frac{1}{4}$ " TO 1'-0" TO DRAIN 2.01-2.12 General Guidelines

Step	Products	Coverage	Dry Mils
1	Metal Lath		
2	P-Tuff™ Sand Slurry (over Metal Lath)	3 gal. / 100 sq.ft.	89 ± 2
3	Sand Broadcast	.	.
4	Topshield™ EST or ALP-150 or Chem-Sentry™ II or Stalntuff™	1 1/4 gal. / 100 sq.ft.	13 ± 2
5	Topshield™ EST or ALP-150 or Chem-Sentry™ II or Stalntuff™	3/4 gal. / 100 sq.ft.	8 ± 2

- Notes:
1. E-Tuff®-100 Base Material is a mixture of 4 part E-Tuff®-100 and 1 part of water by volume.
  2. P-Tuff™ Base Material is a mixture of 4 part P-Tuff™ Classic, SLV, or Flex and 1 part of water by volume.
  3. Repair Crack and Joints 2.09-2.12 General Guidelines

NOT TO SCALE

Rev. 5-31-17



8550 West Desert Inn Road  
 Suite 102-451  
 Las Vegas, NV 89117  
 P | 1-866-977-8833  
 F | 1-800-904-0182  
 www.polytuffus.com  
 sales@polytuffus.com

DETAIL NAME & DESCRIPTION:

**Flexideck E-tuff and P-tuff  
 Metal Lath Wall Termination  
 (Typical)**

DESIGNED

**B. CLANTON**

SHEET

**1 of 1**

DRAWN

**M. HELMANDOTTAR**

SCALE

**N.T.S**

DATE

**5/26/17**

DETAIL NO.

**ML-2**