



No Primer under coating using Plywood

SLOPE DECK Properly Prepared Substrate/
 1/4" TO 1'-0" TO DRAIN 2.01-2.12 General Guidelines

- Notes:
1. E-Tuff®-100 Base Material is a mixture of 4 part E-Tuff®-100 and 1 part of water by volume.
 2. P-Tuff™ Base Material is a mixture of 4 part P-Tuff™ Classic, SLV, or Flex and 1 part of water by volume.
 3. Repair Crack and Joints 2.09-2.12 General Guidelines

Step	Products	Coverage	Dry Mills
1	Enviro-Grip® EP#1 or EP#2 Primer	1 gal. / 300 sq.ft.	3
2	E-Tuff®-100 (with Rubber)	3 gal. / 100 sq.ft.	42 ± 2
3	Sand Broadcast	.	.
4	Poly-Tuff Crete Stencil or Knock Down Finish	1 gal. / 100 sq.ft.	10 ± 2
5	Topshield™ EST or ALP-150 or Chem-Sentry™ II or Stalntuff™ (Recommended)	3/4 gal. / 100 sq.ft.	8 ± 2

NOT TO SCALE

Rev. 5-31-17



8550 West Desert Inn Road
 Suite 102-451
 Las Vegas, NV 89117
 P | 1-866-977-8833
 F | 1-800-904-0182
 www.polytuffus.com
 sales@polytuffus.com

DETAIL NAME & DESCRIPTION:

**Flexideck E-tuff and P-tuff
 Wall Termination
 (Typical)**

DESIGNED

B. CLANTON

SHEET

1 of 1

DRAWN

M. HELMANDOTTAR

SCALE

N.T.S

DATE

5/26/17

DETAIL NO.

WD-2