



NOTES:

1. APPLY PRIMER TO METAL FLASHINGS AT 300 SQ/FT P/GAL AND ALLOW PRIMER TO DRY
2. REMOVE & REPLACE ALL FAILED SEALANT AND INSTALL AS REQ'D.
3. SEAL JOINT FLUSH WITH PTS E-101 JOINT SEALANT
4. APPLY SUPER SEAL TAPE OVER ALL JOINTS IN PLYWOOD
5. APPLY P-TUFF CLASSIC SAND SLURRY AT 8.3 GALLONS P/100 SQ/FT
6. BROADCAST AGGREGATE TO REFUSAL
7. APPLY TOPSHIELD TOP COAT AT 80 SQ/FT P/GALLON

* P-TUFF™ BASE MATERIAL IS A MIXTURE OF 4 PART P-TUFF™ CLASSIC, SLV OR FLEX AND 1 PART OF WATER BY VOLUME

* THE ICC-ES # AND FIRE RATING

* REPAIR CRACKS AND JOINTS 2.09-2.12 GENERAL GUIDELINES



Poly-Tuff Systems International

8550 West Desert In Road
Suite 102-451
Las Vegas, NV 89117
P 1-866-977-8833
F 1-800-804-0182
www.polytuffus.com
sales@polytuffus.com

DETAIL NAME & DESCRIPTION

FLEXIDECK™ P-ML
Heavy Duty Metal Lath Reinforced
Decking System for Wood Substrates

DESIGNED B. CLANTON	SHEET 1 OF 1
DRAWN N. BASTANI	SCALE N.T.S
DATE 5/18/2017	DETAIL NO. P-ML