



TOPSHIELD® ALP-150/ALP-150(SC)

A Single Component, Economical, Aliphatic Topcoat for Concrete and Plywood

1.01 DESCRIPTION

Topshield® ALP-150 is an economical, aliphatic, single-component, liquid-applied, moisture-cured, urethane topcoat for use on concrete and plywood decks. Topshield® ALP-150 is 250 VOC and Topshield® ALP-150 (SC) is 150 VOC. Be sure to use the right product grade that complies with VOC regulations as per federal, state, statutory bodies, county and city regulations/codes at the place of installation of product.

1.02 FEATURES

- UV Stable
- Excellent Weatherability
- Good Color Retention

1.03 TYPICAL USES

- Pedestrian Traffic
- Concrete or Plywood Decks
- Resealing Existing Urethane Surfaces
- Most Metal, Wood, or Masonry Surfaces

1.04 COLORS

Contact PSI for availability as not a stocked product.

Light gray, medium gray, dark gray, tan, dark tan, chocolate Custom colors are also available. Minimum order required. Please contact PSI for details. See color chart for special provisions.

1.05 PACKAGING

1 gallon (3.78 liter) can
5 gallon (19 liter) pail
55 gallon drum, net fill 50 gallons (189 liters)

1.06 MIXING

Before application, mix Topshield® ALP-150 using a mechanical mixer (Jiffy Mixer) at slow speeds or by hand for at least 5 minutes. Mix Topshield® ALP-150 thoroughly until a homogeneous mixture and color is obtained. When using a color pack system, "boxing" from one mixed pail to the next is recommended. Always save 1 (3.78 liters) gallon or more and mix into the next pail to prevent color variation. Likewise, with pre-tinted topcoats, mix the last gallon or two from the previous batch into the new batch number. Box the last gallons of the last used batch numbers with the new batch number to prevent hue or shading variation.

1.07 SURFACE PREPARATION

Refer to General and Safety Guidelines for complete information. Install a 100-200 sqft (9.3-18.6 sqm) mock up of the system to be installed and approve for aesthetics, color, slip resistance, actual coverage rates and functionality before proceeding.

APPLICATION

2.01 APPLICATION BASICS

The first coat of Topshield® ALP-150 should be applied at the rate of 1 gallon/100 sqft or 100 sqft/gallon (0.41 liters/m²). For best results, airless sprayer or phenolic-core-roller may be used, but extra care should be taken not to cause air bubbles. Apply Topshield® ALP-150 evenly over the entire deck resulting in 11±2 dry mils (278±50 microns). After 24 hours, proceed to the second coat.

Topshield® ALP-150 may require more than one coat depending on the job specifications and requirements. When estimating material requirements, coverage rates tend to increase for subsequent coats of material. To obtain proper adhesion between coats it is imperative that re-coating be done within 48 hours.

Refer to individual Systems Description under System Specifications Section of the Poly-Tuff Systems International (PSI) catalog or website for specific coverage rates.

Coverage rates and cure times will vary depending on temperature, relative humidity, surface roughness and porosity, aggregate selection and embedment, and application technique. Coverage rates provided are optimal and are not guaranteed.

2.02 CURING

At 75°F (24°C) and 50% relative humidity, allow each coat to cure a minimum of 16 hours between each coat. If more than 48 hours passes between coats, reprime the surface with PSI Primer before proceeding.

Allow 24 hours before permitting light pedestrian traffic and at least 72 hours before permitting heavy pedestrian or vehicular traffic on to the finished surface.

Uncured Topshield® ALP-150 is very sensitive to heat and moisture. Higher temperatures and/or high humidity will accelerate the cure time. Use caution in batch sizes and thickness of application. Low temperature and/or low humidity extend the cure time. To accelerate cure, topcoat accelerator may be used.

2.03 EQUIPMENT CLEANUP

Equipment should be cleaned with an environmentally-safe solvent, as permitted under local regulations, immediately after use.

2.04 STORAGE

Topshield® ALP-150 has a shelf life of one (1) year from date of manufacture when stored indoors at a temperature between 60°F to 95°F (15°C to 35°C) in original, factory-sealed containers.

2.05 LIMITATIONS

- Surfaces must be dry, clean and free of foreign matter.
- Surface may be slippery when wet. Topshield® ALP-150 may become flat and stained over time.
- Topshield® ALP-150 has limited chemical resistance properties.

- Containers that have been opened must be used as soon as possible.
- Do not dilute under any circumstance.
- The following conditions must not be coated with PSI deck coating systems or products: on grade or below grade slabs, split slabs with buried membrane, sandwich slabs with insulation, slabs over unvented metal pan, suspended pool, swimming pool decks without the use of Enviro-Grip™ 404FC primer and asphalt surfaces, asphalt overlays without the express written consent of PSI.
- PSI Deck Coating is not recommended over magnesite, gypsum lightweight and where chained or studded tires may be used.

WARNING: This product contains isocyanates and solvent.

TECHNICAL DATA: Based on Draw Down Film

Topshield ALP-150	
250 VOC. (Based on draw down film).	
Coverage Rate	1 gallon/100 sqft (0.41 L/m ²)
Dry Film Thickness	
Per Coat @ 1 gallon/100 sqft	12 ± 2 dry mils 305 ± 50 microns
Hardness, ASTM D-2240	90 ± 5 Shore A
Tear Resistance, Die C, ASTM D-624	400 ± 50 pli 70 ± 8.8 kNm
Tensile Strength, ASTM-D412	2700 ± 300 psi 18.6 ± 2 MPa
Specific Gravity	1.16 ± 0.1
Total Solids by Weight, ASTM D-2369	80 ± 2%
Total Solids by Volume, ASTM D-2697	74 ± 2%
Viscosity at 75°F (24°C)	2500 ± 700 cps
Volatile Organic Compounds, ASTM D-2369-81	1.875 lbs/gal 225 gm/liter
Elongation ASTM D-412	200 ± 50
Solar Reflective Index	90

Topshield ALP-150 (SC)	
100 VOC. (Based on draw down film).	
Coverage Rate	1 gallon/100 sqft (0.41 L/m ²)
Dry Film Thickness	
Per Coat @ 1 gallon/100 sqft	12 ± 2 dry mils 305 ± 50 microns
Hardness, ASTM D-2240	90 ± 5 Shore A
Tear Resistance, Die C, ASTM D-624	400 ± 50 pli 70 ± 8.8 kNm
Tensile Strength, ASTM-D412	2700 ± 300 psi 18.6 ± 2 MPa
Specific Gravity	1.20 ± 0.1
Total Solids by Weight, ASTM D-2369	85 ± 2%
Total Solids by Volume, ASTM D-2697	83 ± 2%
Viscosity at 75°F (24°C)	3500 ± 700 cps
Volatile Organic Compounds, ASTM D-2369-81	0.825 lbs/gal 99 gm/liter
Elongation ASTM D-412	200 ± 50
Solar Reflective Index	90

Please read all information in the General & Safety Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. PSI Products are for "Professional Use Only" and preferably applied by professionals who have prior experience with the PSI Products or have undergone training in application of PSI Products. Published technical data and instructions are subject to change without notice. Contact your local PSI representative or visit our website for current technical data, instructions, and project specific recommendations.

LIMITED WARRANTY

PSI warrants its products to be free of manufacturing defects and that they will meet PSI current published physical properties. PSI warrants that its products, when properly installed by a state licensed waterproofing contractor according to PSI guide specifications and product data sheets over a sound, properly prepared substrate, will not allow water migration for a period of 12 months. Seller's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by PSI of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. PSI shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. PSI shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. PSI reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and PSI makes no claim that these tests or any other tests, accurately represent all environments.