



# B-TUFF® GROUT NS

## Non-shrink, Non-metallic, Multi-purpose Flowable Grout

### 1.01 DESCRIPTION

**B-Tuff® Grout NS** is a non-shrink, non-corrosive, non-metallic, multipurpose, cement based, flowable grout. TuffGrout™ NS is formulated for a wide variety of grouting applications, from damp pack to flowable through a controlled, positive expansion. Please use the correct product grade that complies with VOC regulations as per federal, state, county and city regulations/codes at the place of installation of product.

### 1.02 USES

- Anchoring
- Machinery Grouting
- Pre-Cast Walls
- Pump And Equipment Based Column Base Plates
- Sign Posts, Dowels, Guard Rails, Bolts
- Tilt-Up Walls

### 1.03 FEATURES

- Can Be Extended with Pea Stone For Deep Applications
- Can Contribute to Leed Credits
- Chloride and Gypsum-Free
- Controlled Positive Expansion for Maximum Effective Bearing
- Easy To Use, Simply Add Water
- Excellent Freeze/Thaw Resistance
- Natural Concrete Gray
- Non-Corrosive/Will Not Rust
- Non-Metallic
- Pourable/Pumpable Versatility
- USDA Accepted

### 1.04 TECHNICAL DATA

Corp of Engineers CRD-C-621 Grade A, B & C ASTM C-107. Grade A, B & C

### 1.05 COLOR

Natural Concrete Gray

### 1.06 PACKAGING

50 lbs (22.7 kgs) multiple-plastic-lined bags

### 1.07 COVERAGE GUIDE

50 lbs (22.7 kgs) multiple-plastic-lined bag will yield approximately 0.45 cuft (0.012 cum) in a fluid condition. 50% by weight extension (25 lbs or 11.34 kgs) of 3/8" (0.96 cm) pea stone will yield approximately 0.59 cuft (0.0167 cum).

### 1.08 PREPARATION

Remove all dirt, oil, and loose or foreign material. Any metal in contact with **B-Tuff® Grout NS** must be free of rust, oil, grease, and other foreign matter which would limit bond. Concrete surface must be sound and roughened to ensure proper bonding. Prior to placing **B-Tuff® Grout NS**, the surface must be saturated surface dry (SSD), if possible for an hour. Remove all excess water before placement of grout. Bolts,

base plates and equipment must be secure and rigid before placement of **B-Tuff® Grout NS**. All materials and surfaces in contact with the grout should be conditioned between 50-80°F (10-26.66°C) for proper performance. Provide heating or cooling, as necessary, to compensate for temperature extremes and changes in cure time.

Forms: Allow for the continuous placement of **B-Tuff® Grout NS**. Provisions for venting to avoid air entrapment must be made. Placing from one side, provide a 45° angle in the forms to a height suitable to provide a head of grout during placement. On all sides, provide a minimum 1" (2.54 cm) horizontal clearance between the base plate and forms. Forms should be at least 1" (2.54 cm) higher than the bottom of the base plate.

### 1.09 MIXING

Small quantities of **B-Tuff® Grout NS** may be hand mixed in a concrete mixing pan until lump free. For large quantities and continuous pours, mix using a mortar mixer with rubber tipped blades or appropriate grout pump for a minimum of 5 minutes. Start with minimum water requirements. Always add water to mixer first, then slowly add powder. Use only the amount of water required for the desired placement consistency. Mix in two steps: Add 2/3 of the water, add **B-Tuff® Grout NS**, after partial mixing add the remaining 1/3 of the water for desired consistency. Thoroughly mix total quantity for an additional 2 to 3 minutes. Do not mix more than can be placed before in 40 minutes.

### 1.10 APPLICATION

Place continuously and quickly. Start from one side to avoid air entrapment. Be sure **B-Tuff® Grout NS** fills spaces and remains in contact with the plate. DO NOT VIBRATE. A minimum of 1" (2.48 cm) vertical clearance should be maintained for base plate grouting applications. Thinner vertical clearances may require the use of another type of grout.

Deep application: Pre-washed and graded 3/8" (0.96 cm) pea gravel should be used in large applications (greater than 1' x 1' or 30.4 cm x 30.4 cm) and thicker than 3" (7.62 cm) as follows:

3"-5" (7.62-12.7 cm): Add 25% of 3/8" (0.96 cm) pea gravel per 50 lbs (22.68 kgs) bag of grout.

5" (12.7 cm) and over: Add 50% of 3/8" (0.96 cm) pea gravel per 50 lbs (22.68 kgs) bag of grout. Place in 6" (15.24 cm) lifts with proper reinforcement.

### 1.11 CURING

Immediately cover with clean, wet rags and keep moist until final set. After final set, remove rags and apply an ASTM-C309 curing compound.

#### Special Conditions

**Hot weather conditions:** Accelerates setting time and causes premature drying of the grout. Keep the grout cool. Store unopened bags in the shade. Provide shade for the area to be grouted. Use cool or chilled mixing water. Protect grout from direct sun exposure for up to 24 hours after grouting. For additional information, refer to ACI 305 (Recommended Practices for Hot Weather Concreting).

**Cold weather conditions:** Retards strength gain and set time. Warm the grout above 50°F (10°C). Raise the temperature of the area to be grouted with space heaters or steam. Warm the mixing water. Cover and insulate the grout to retain warmth. The minimum temperature (ambient, substrate, and grout) for grouting is 40°F (5°C) unless special provisions are followed. For additional information, refer to ACI 306 (Recommended Practices for Cold Weather Concreting).

### 1.12 CLEAN UP

Tools and Equipment: Clean with water or PSI's **EnviroClean™**.

### 1.13 STORAGE AND SHELF LIFE

The material should be stored between 40–95°F (4–35°C) in a cool, dry area away from direct sunlight. The shelf life of properly stored, unopened containers is 12 months from date of manufacture. An excessive temperature differential and/or high humidity can shorten the shelf life expectancy.

### 1.14 LIMITATIONS

- DO NOT place at temperatures below 40°F (5°C) unless special provisions are followed. At low temperatures, water requirement should be field tested.
- When nearby equipment causes vibration of the grout, during the set, such equipment should be shut down for a period of 24 hours.
- DO NOT mix over 5 minutes.
- DO NOT over water; this can cause bleeding or separation.
- DO NOT retemper.
- DO NOT add cement, sand, or admixtures.
- Avoid hazards by following all precautions found in the Safety Data Sheets (SDS), product labels, and technical literature.
- Do not dilute.

- Wear protective gloves and goggles.
- Avoid prolonged skin contact.

**DO NOT EXPOSE TO OR APPLY NEAR FIRE OR FLAMES. FOR WELL VENTILATED OR EXTERIOR USE ONLY!**

**READ SDS PRIOR TO USING PRODUCT. FOR PROFESSIONAL USE ONLY. KEEP OUT OF REACH OF CHILDREN. MADE IN THE USA.**

PHYSICALS						
Flexural Strength (ASTM C78) @ 28 days	1415 psi (9.99 MPa)					
Tensile Strength (ASTM C190) @ 28 days	620 psi (4.3MPa)					
Split Tensile Strength ASTM C469 28 Days	735 psi (4.20 MPa)					
	Plastic		Flowable		Fluid	
Water per 50 lbs	6.30-6.85 pints	2.98-3.25 liters	6.85-7.75 pints	3.25-3.68 liters	7.75-8.35 pints	3.68-3.95 liters
Comprehensive Strength ASTM C109						
1 Day	4,000 psi	27.58 MPa	3,100 psi	21.37 MPa	1,450 psi	9.99 MPa
3 Days	5,500 psi	37.92 MPa	5,000 psi	34.47 MPa	3,700 psi	25.51 MPa
14 Days	8,100 psi	55.85 MPa	6,900 psi	47.57 MPa	6,200 psi	42.75 MPa
28 Days	10,200 psi	70.32 MPa	8,400 psi	57.92 MPa	8,100 psi	55.85 MPa
Expansion Percentage % ASTM C1090						
1 Day	0.07		0.03		0.02	
3 Days	0.07		0.03		0.02	
14 Days	0.07		0.03		0.02	
28 Days	0.07		0.03		0.02	
<b>Note:</b> The data shown is based on controlled laboratory testing. Reasonable variation from test results shown can be expected. Field and laboratory testing should be controlled on the basis of the desired placing consistency, rather than strictly on water content.						

Please read all information in the General & Safety Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. PSI Products are for "Professional Use Only" and preferably applied by professionals who have prior experience with the PSI Products or have undergone training in application of PSI Products. Published technical data and instructions are subject to change without notice. Contact your local PSI representative or visit our website for current technical data, instructions, and project specific recommendations.

#### LIMITED WARRANTY

PSI warrants its products to be free of manufacturing defects and that they will meet PSI current published physical and chemical properties. Seller's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by PSI of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. PSI shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. PSI shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. PSI reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

#### DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and PSI makes no claim that these tests or any other tests, accurately represent all environments.