



SLOPE PLYWOOD/OSB  
 $\frac{1}{4}$ " TO 1'-0" TO DRAIN

- Notes:
1. E-Tuff®-100 Base Material is a mixture of 4 part E-Tuff®-100 and 1 part of water by volume.
  2. P-Tuff™ Base Material is a mixture of 4 part P-Tuff™ Classic, SLV, or Flex and 1 part of water by volume.
  3. Repair Crack and Joints 2.09-2.12 General Guidelines

| Step | Products   | Coverage                | Dry Mils |
|------|--|-------------------------|----------|
| 1    | Metal Lath   |                         |          |
| 2E   | E-Tuff®-100 Sand Slurry (over Metal Lath)                  | 6 gal. / 100 sq.ft.     | 95 ± 2   |
| 2P   | P-Tuff™ Sand Slurry (over Metal Lath)                      | 6 gal. / 100 sq.ft.     | 89 ± 2   |
| 3    | Sand Broadcast   | .                       | .        |
| 4    | Topshield™ EST or ALP-150 or Chem-Sentry™ II or Stalntuff™ | 1 1/4 gal. / 100 sq.ft. | 13 ± 2   |
| 5    | Topshield™ EST or ALP-150 or Chem-Sentry™ II or Stalntuff™ | 3/4 gal. / 100 sq.ft.   | 8 ± 2    |

NOT TO SCALE Rev. 5-31-17



8550 West Desert Inn Road  
 Suite 102-451  
 Las Vegas, NV 89117  
 P | 1-866-977-8833  
 F | 1-800-904-0182  
 www.polytuffus.com  
 sales@polytuffus.com

DETAIL NAME & DESCRIPTION:  
**Flexideck E-tuff and P-tuff  
 Metal Lath Edge Termination  
 (Typical)**

|                                 |                           |
|---------------------------------|---------------------------|
| DESIGNED<br><b>B. CLANTON</b>   | SHEET<br><b>1 of 1</b>    |
| DRAWN<br><b>M. HELMANDOTTAR</b> | SCALE<br><b>N.T.S</b>     |
| DATE<br><b>5/25/17</b>          | DETAIL NO.<br><b>ML-1</b> |