



NOTES:

1. APPLY PRIMER TO CONCRETE AND METAL FLASHINGS AT 300 SQ/FT P/GAL AND ALLOW PRIMER TO DRY
2. APPLY PRIMER AND ALLOW PRIMER TO DRY
3. APPLY P-TUFF CLASSIC AT 40 SQ/FT P/GALLON
4. APPLY P-TUFF CLASSIC AT 100 SQ/FT P/GALLON
5. BROADCAST AGGREGATE TO REFUSAL
6. APPLY COMPLETE FLEXIDECK SYSTEM AS SPECIFIED

- * P-TUFF™ BASE MATERIAL IS A MIXTURE OF 4 PART P-TUFF™ CLASSIC, SLV OR FLEX AND 1 PART OF WATER BY VOLUME
- * THE ICC-ES # AND FIRE RATING
- * REPAIR CRACKS AND JOINTS 2.09-2.12 GENERAL GUIDELINES



8550 West Desert In Road
 Suite 102-451
 Las Vegas, NV 89117
 P 1-866-977-8833
 F 1-800-804-0182
 www.polytuffus.com
 sales@polytuffus.com

DETAIL NAME & DESCRIPTION
FLEXIDECK™ P-TW
ICC-ES #ESR-2785
 Tile-Underlayment
 Waterproofing System-Concrete

DESIGNED B. CLANTON	SHEET 1 OF 1
DRAWN N. BASTANI	SCALE N.T.S
DATE 5/18/2017	DETAIL NO. P-TW