



P-TUFF® U75

Fast Curing, 100% Solids, Flexible, Aliphatic, Seamless, Two Component Spray Polyurea Coating System

1.01 DESCRIPTION

P-Tuff® U75 is a fast set, rapid curing, 100% solids, flexible, aliphatic, two component, spray polyurea that can be applied to suitably prepared interior or exterior concrete and metal surfaces. Its extremely fast gel time makes it suitable for applications down to -20°F (-29°C). It may be applied in single or multiple applications without appreciable sagging and it is relatively tolerant to moisture and temperature variances, allowing application in most temperatures. Please use the correct product grade that complies with VOC regulations as per federal, state, county and city regulations/codes at the place of installation of product.

1.02 FEATURES

- Coats Carbon or Mild Steel Metals Without Primer
- Elastomeric
- Good Chemical Resistance
- Installed With or Without Reinforcement in Transitional Areas
- Interior or Exterior Applications
- Meets USDA Criteria
- Non-Reactive
- Seamless
- Excellent Color Retention
- Low Temperature Flexibility
- No Toxic Vapors
- Odorless
- Zero VOC (100% Solids)

1.03 USES

- Airports
- Fertilizer Plants
- Industrial Facilities
- Manufacturing Facilities
- Mining Operations
- Parking Garage Decks
- Refineries
- Structural Steel
- Warehouse Floors
- Water & Waste Water Treatment
- Cold Storage Facilities
- Food Processing Plants
- Landfill Containment
- Marine Environments
- Paper & Pulp Mills
- Power Plants
- Secondary Containment
- Walkways & Balconies

1.04 COLOR

Various colors are available upon request. Minimum quantity REQUIRED

1.05 PACKAGING

- 10-gallon kit: 5 gallon (18.9 liters) pail of Side-A and 5-gallon (18.9 liters) pail of Side-B.
- 100-gallon kit: 50 gallon (189 liters) drum of Side-A and 50-gallon (189 liters) drum of Side-B.

1.06 COVERAGE

P-Tuff® U75 may be applied at any rate to achieve desired thickness. Theoretical coverage for 1 mil thickness is one gallon per 1600 sqft (25.4 microns is 3.78 liters/149 sqm).

1.07 SURFACE PREPARATION

In general, coating performance and adhesion are directly proportional

TECHNICAL DATA (Based on draw down films)

Pot Life @150-160°F (65.5-71°C), 50% R.H.	4 - 8 sec
Tack Free Time (thickness & substrate temperature dependent)	6 - 120 sec
Viscosity at 150-160°F (66.5-71°C)	Side-A: 120 ± 20 cps Side-B: 40 ± 20 cps
Density (Side A & B Combined)	8.5 lbs/gal
Flash Point	> 200°F (93.3°C)
Tensile Strength, ASTM D-412*	3300 ± 300 psi (23 ± 1.4 MPa)
Volatile Organic Compounds, ASTM D-2369-81	0.0 lbs/gal (0 gm/liter)
Hardness, ASTM D-2240 Shore D	50 ± 5
Elongation, ASTM D-412*	220 ± 20%
Tear Resistance, ASTM D-412*	400 ± 20 pli (70.1 ± 3.5 kN/m)
Service Temperature - Dry	-40°F to 300°F (-40 to 148.9°C)
Service Temperature - Wet	40°F to 120°F (4.4 to 48.9°C)
Water Absorption, ASTM D471 (maximum 77°F, 24 hours)	< 0.5%
Taber Abrasion Resistance, ASTM D4060 (CS17 wheel, 1000 cycles, 1 kg load) (maximum)	33 mg loss
Crack Bridging, ASTM C836 (-13°F, 1.6mm crack, 25 cycles)	Pass
Pull-Off Strength (minimum), ASTM D4541:Inter-Coat Adhesion (within recoat time)	Excellent
Concrete (Shotblasted profile), substrate failure occurred	>500 psi (3.4 MPa)
Concrete (Primed), substrate failure occurred	>500 psi (3.4 MPa)
Steel (90 µm blast profile)	>900 psi (6.2 MPa)
Lineal Shrinkage	1 - 2%
Flexibility (1/8" [3mm] Mendrel Bend Test), ASTM D1737	Pass

Resistance to Weathering, ASTM G-23 (Type QUV Weatherometer-3000 hrs exposure)
No cracking or blistering. Color change, gloss reduction & chalking are noted.

(*These physical properties from sample sprayed with Graco EXP2 @ 2000 psi minimum, with Fusion Gun AR4242 @ 150-160°F (65°C to 71°C). Different machine and parameter will change these properties. User should perform their own independent testing as properties are approximate).

to surface preparation. Most failures in the performance of surface coatings can be attributed to poor surface preparation. Polyurea coatings rely on the structural strength of the substrate to which they are applied. All surfaces must be free of dust, dirt, oil, grease, rust, corrosion and other contaminants. When coating substrates previously used, it is important to consider the possibility of substrate absorption, which may affect the adhesion of the coating system, regardless of the surface preparation. PSI recognizes the potential for unique substrates from one project to another. The following information is for general reference, and for project-specific questions, contact a PSI representative.

New and Old Concrete:

Refer to SSPC-SP13/NACE 6, or ICRI 03732: CSP 3-5. New concrete must be cured for 28 days prior to product application. Surface must be clean, dry, sound and offer sufficient profile for product adhesion. Remove all dust, dirt, oil, form release agents, curing compounds, salts, efflorescence, laitance and other foreign matter by shotblasting and/or suitable chemical means, in accordance with local chemical regulations. Rinse thoroughly, to achieve a pH between 8.0 and 11.0. Allow to dry completely. If old concrete has a surface that has deteriorated to an unacceptably rough surface, P-Tuff® U75 or a mixture of Enviro-Grip™ #1 and sand should be used as a repair agent for cracks, spalls, bug holes and voids. Upon full cure of the repair agent, prime the entire surface intended for coating. Concrete Surface Preparation Reference:

- ASTM D4258 – Standard practice for cleaning concrete
- ASTM D4259 – Standard practice for abrading concrete
- ASTM D4260 – Standard practice for etching concrete
- ASTM F1869 – Standard test method for measuring moisture vapor emission rate of concrete
- ICRI 03732 – Concrete surface preparation

Wood:

All wood should be clean, dry and free of any knots, splinters, oil, grease or other contaminants. Splintered or rough areas should be sanded. Knots should be repaired using P-Tuff® U75 with sand. Upon full cure of the repair agent, prime the entire surface intended for coating.

Steel (Atmospheric and Immersion Exposure):

Remove all oil, grease, weld spatters and round off any sharp edges from surface. Minimum surface preparation is Near White Metal Blast Cleaning per SSPC-SP10/NACE 2. Optimum surface profile is 2-3 mils. Prime and shoot P-Tuff® 75 on to any bare metal the same day as it is cleaned to minimize any potential flash rusting.

Rough and pinholed concrete surfaces may require more primer. Discovery of these issues is generally revealed in the mockup. See the Tech-Note Section of the Poly-Tuff website. Do not allow primer to puddle, dry roll excess primer with a dry nap roller to pick up excess primer in puddles and overlaps.

Refer to General & Safety Guidelines for complete information.

1.08 PRIMING

Prime surface as required with Enviro-Grip™ EP#2(SC), #1 or PUR#555 at a rate of 1 gallon/300 sqft or 300 sqft/gallon (0.14 liters/sqm). Apply

using a brush or phenolic core roller. This will result in 3 dry mils (76 microns) of coating. Existing urethane coated surfaces should be primed with Enviro-Grip™ PUR#555.

Rough and pinholed concrete surfaces may require more primer. Discovery of these issues is generally revealed in the mockup. See the Tech-Note Section of the Poly-Tuff website. Do not allow primer to puddle, dry roll excess primer with a dry nap roller to pick up excess primer in puddles and overlaps.

1.09 MIXING

P-Tuff® U75 may not be diluted under any circumstances. Use appropriate solvent for solvent purge line and flushing of equipment and if spraying stops for periods exceeding the pot life of the material. Thoroughly mix P-Tuff® U75 Side-B Base material with air driven power equipment until a homogeneous mixture and color is attained.

1.10 JOINTS, CRACKS, AND FLASHING

Apply P-Tuff® U75 over all primed joints and cracks. Bridge the joints and cracks with 4" (10.16 cm) Super Seal Polyester Tape. Do not prime over Super Seal Tape. Over reinforcement tape apply a thin coat of P-Tuff® U75 and smooth onto adjacent surface. Optionally in lieu of 3 coursing laps and joints, Super Seal Tape may be used over all cleaned laps, joints and cracks and then coated. Fully reinforced systems do not require the use of Super Seal Tape over joints and cracks.

Wall to deck perimeter flashings shall be either a minimum of 24 gauge galvanize steel flashing or 40-60 mil EPDM Sheet Rubber. Flashing shall turn up the wall a minimum of 6" (15.24 cm) and turn out 4" (10.16 cm) onto the deck surface. Metal Flashings require Enviro-Grip™ EP#2. EPDM must be primed with Enviro-Grip™ #1, #2, or PUR#555. The use of Flexi-Flashing™ may often replace corrosive metal flashings.

APPLICATION

2.01 APPLICATION BASICS

P-Tuff® U75 should be applied using a 1:1 plural component equipment capable of developing a minimum of 2000 psi and heating the individual component to 170°F (77°C) using an impingement gun. Hose temperature should be maintained at 160-170°F (71-77°C). The P-Tuff® U75 material should be preheated to 75- 85°F (24-30°C).

P-Tuff® U75 should be sprayed in multi directional passes for a proper uniform thickness.

Recoat Time	0-6 hours
Recommended Applied Thickness	> 2 mm
Return to Service: Foot Traffic	2 - 4 hours
Return to Service: Full Service	> 24 hours

2.02 EQUIPMENT CLEANUP

Equipment should be cleaned immediately after use with an environmentally safe, urethane-grade solvent (alcohol free) as permitted under local regulations.

2.03 SHELF LIFE AND STORAGE

P-Tuff® U75 has a shelf life of 12 months from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C).

Avoid freezing temperatures. Store drums on wooden pallets to avoid direct contact with the ground. If stored for a long period of time,



rotate Side-A and Side-B drums regularly.

2.04 - LIMITATIONS

- Surfaces must be dry, clean and free of foreign matter.
- Containers that have been opened must be used as soon as possible.
- Do not open until ready to use.
- Side-A and Side-B containers should be fitted with a desiccant cartridge on the pail so that only dry air is sucked in a pail while withdrawing product.

This product is considered Dangerous Goods.

DOT regulations classify it as Side-A: UN 2810, TOXIC LIQUID, organic, N.O.S (Isophorone Di-isocyanate), Class 6.1, PG III, TOXIC Side-B: UN 2735, AMINES, liquid corrosive, N.O.S (polyoxypropylenediamine), Class 8, PG III, CORROSIVE

WARNING: THIS PRODUCT CONTAINS ISOCYANATES AND CURATIVES.

Please read all information in the General & Safety Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. PSI Products are for "Professional Use Only" and preferably applied by professionals who have prior experience with PSI Products or have undergone training in application of PSI Products. Published technical data and instructions are subject to change without notice. Contact your local PSI representative or visit our website for current technical data, instructions, and project specific recommendations.

LIMITED WARRANTY

PSI warrants its products to be free of manufacturing defects and that they will meet PSI current published physical and chemical properties. Seller's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by PSI of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. PSI shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. PSI shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. PSI reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and PSI makes no claim that these tests or any other tests, accurately represent all environments.

© 2020 Poly-Tuff Systems International Corp. All rights reserved. REV20201007.AG