

TuffCoat FD

Smooth or Textured Epoxy Flooring System



- 1| Concrete slab should be etched, cleaned, and prepared for coating application to an ICRI profile of CSP 1, with TuffPrep etcher/cleaner. TuffClean should be used for any dirt, oil, or grease build up.**
- 2| TuffPatch VOH / TuffDeck II / or TuffTop SL. If required any of these materials may be used to expedite spall repairs or floor leveling.**
- 3| TuffCoat FD Base Coat – Apply first coat @ 100 sf per gallon. If desired, broadcast preselected aggregate immediately.**

- 4| Aggregates – Sands, colored quartz, aluminum oxides, etc. can be used and applied to achieve the desired texture and effect.**
 - 5| Tuff Coat FD Top Coat– Clear or pigmented. Apply topcoat @ 150 sf per gallon after base coat has become tack free to the touch but within 12 hours. Open to traffic after a full 24 hour cure time.**
- TuffCoat FD is designed for sealing interior and exterior slabs, tanks, holding ponds, and steel from water chloride and chemical attack.