

POLY-TUFF SYSTEMS INTERNATIONAL

2250 E. Tropicana Ave
Suite 19-600
Las Vegas, NV 89119



Phone: (866) 977-8833
Fax: (800) 804-0182
Email: sales@polytuffus.com
Web: www.polytuffus.com

PSI Tech-Note

From the Desk of Bob Clanton

September 6, 2007

Single Component Solvent Base Coatings Applied Over E-101 and E-102 Sealants

PTS-E-101 and PTS-E-102 Sealants must be cured for a minimum of 24 hours before applying any solvent based coatings over the sealant. An application of primer may be applied as a separating coat between the primer and sealant. PSI recommends that field adhesion tests are applied before proceeding to over-coating the PTS Sealants.

It is permissible to apply paint or coating directly over E-101 and E-102 Sealants with water based paints or coatings.

PSI offers lab tests of the coatings and sealant compatibility quality assurance and compatibility. Please call 866.977.8833 for Technical Service.